



COATEX IR MAT BLANK

Single component PU anti-graffiti coating

- Hard, scratch-resistant coating makes it easy to remove graffiti
- Does not yellow or chalk
- Virtually odourless
- Transparent protective layer
- For non-absorbent surfaces

COATEX IR MAT BLANK

BESKRIVELSE

A one-component, moisture-curing, low-solvent, transparent protective agent and polyurethane anti-graffiti coating based on polyurethane.

ANBEFALT BRUK

Coatex IR is suitable as a durable protective coating. Its excellent chemical resistance makes it an excellent anti-graffiti coating. Can be used on all smooth, slightly absorbent surfaces, such as coating systems, acrylic wall paints, on bare concrete or primed concrete, polyester glass fibre, and various thick sheet materials. Coatex IR can be used indoors because it does not contain solvents.

ANBEFALT SYSTEM

Untreated substrate:
first layer: Curaton CC (optional)
second layer: Coatex IR Mat Blank
third layer: Coatex IR Mat Blank (optional)

Treated surface:
first layer: Coatex IR Mat Blank
second layer: Coatex IR Mat Blank

TEKNISKE DATA

Tetthet:	1,17 kg/l
Glansgrad:	Matt
Tørrstoffinnhold i vekt:	99%
Tørrstoffinnhold i volum:	99%

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Håndterbar:	4 hours
Overmalbar:	12 hours
Herdetid:	3 days

ANBEFALT TØRRFILMTYKKELSE

100 µm

TEORETISK FORBRUK

10 m² / l with a dry layer thickness of 100 microns.

PRAKTISK FORBRUK

The actual consumption is dependent on the method of application.

BRUKSANVISNING

Apply Coatex IR using a short-haired roller or brush. Apply the product in one or two thin layers (maximum layer thickness = 100 µm per layer). Before applying a second layer, wait 12 hours, but no longer than 24 hours. Replace the roller and tray every half hour and make sure the used packaging is properly closed while working. This will prevent the product from becoming less viscous (i.e. thixotropy). Exceeding the recommended layer thickness can generate light foam.

PÅFØRINGSBETINGELSER

Minimum ambient temperature : 5 °C
Maximum relative humidity : 100%
Minimum surface temperature : 5 °C
Maximum surface temperature : 35 °C

RENGJØRING AV UTSTYR/SPILL

Rinse with Graffitiex 4 immediately after use.

MERKNADER

Sheen: Transparent matt/low silky gloss.
Dispose of the remaining product and empty packaging as chemical waste in accordance with the local regulations and legal requirements.

SIKKERHETSDATA

VOC nivå:	10 g/l
VOC ferdigblandet:	10 g/l
VOC kategori:	A/i
VOC grense:	500 g/l

Merknader angående sikkerhet: Consult the associated product safety leaflet and the information listed on the packaging.

HOLDBARHET

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Utstedt dato: 05/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfeldige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu