



COATEX IR MAT BLANK

Single component PU anti-graffiti coating

- Hard, scratch-resistant coating makes it easy to remove graffiti
- Does not yellow or chalk
- Virtually odourless
- Transparent protective layer
- For non-absorbent surfaces

COATEX IR MAT BLANK

BESKRIVNING

A one-component, moisture-curing, low-solvent, transparent protective agent and polyurethane anti-graffiti coating based on polyurethane.

REKOMMENDERAD ANVÄNDNING

Coatex IR is suitable as a durable protective coating. Its excellent chemical resistance makes it an excellent anti-graffiti coating. Can be used on all smooth, slightly absorbent surfaces, such as coating systems, acrylic wall paints, on bare concrete or primed concrete, polyester glass fibre, and various thick sheet materials. Coatex IR can be used indoors because it does not contain solvents.

REKOMMENDERAT SYSTEM

Untreated substrate:
first layer: Curaton CC (optional)
second layer: Coatex IR Mat Blank
third layer: Coatex IR Mat Blank (optional)

Treated surface:
first layer: Coatex IR Mat Blank
second layer: Coatex IR Mat Blank

TEKNISK DATA

Densitet:	1,17 kg/l
Glansnivå:	Matt
Torrsubstansvikt:	99%
Torrsubstansvolym:	99%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Hanteringstorr:	4 hours
Övermålningsbar:	12 hours
Fullt härdad:	3 days

REKOMMENDERAD TORRFILMSTJOCKLEK

100 µm

TEORETISK FÖRBRUKNING

10 m² / l with a dry layer thickness of 100 microns.

PRAKTISK FÖRBRUKNING

The actual consumption is dependent on the method of application.

BRUKSANVISNING

Apply Coatex IR using a short-haired roller or brush. Apply the product in one or two thin layers (maximum layer thickness = 100 µm per layer). Before applying a second layer, wait 12 hours, but no longer than 24 hours. Replace the roller and tray every half hour and make sure the used packaging is properly closed while working. This will prevent the product from becoming less viscous (i.e. thixotropy). Exceeding the recommended layer thickness can generate light foam.

APPLICERINGSFÖRHÅLLANDEN

Minimum ambient temperature : 5 °C
Maximum relative humidity : 100%
Minimum surface temperature : 5 °C
Maximum surface temperature : 35 °C

RENGÖRING AV UTRUSTNING/SPILL

Rinse with Graffitec 4 immediately after use.

ANMÄRKNINGAR

Sheen: Transparent matt/low silky gloss.
Dispose of the remaining product and empty packaging as chemical waste in accordance with the local regulations and legal requirements.

SÄKERHETSDATA

VOC-nivå:	10 g/l
VOC färdigmix:	10 g/l
VOC-kategori:	A/i
VOC-gräns:	500 g/l

Anmärkningar om säkerhet: Consult the associated product safety leaflet and the information listed on the packaging.

HÅLLBARHET

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Utgivet den: 05/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu