



COATEX SPECIAAL NV

Anti-graffiti coating in matt or gloss

- Very durable, scratch resistant, and chemically resistant
- Flexible and shock-resistant
- Does not yellow, UV resistant
- Available in matt and gloss, colourless, and with colour
- Colourless coating does not change the appearance of the surface



COATEX SPECIAAL NV

OPIS

Polyurethane two-component scratch-resistant anti-graffiti coating with good chemical and mechanical resistance and colour fastness.

ZALECANE UŻYCIE

Coatex Special NV is a durable anti-graffiti system for objects that must comply with the strictest requirements in terms of chemical and mechanical resistance.

REMOVING GRAFFITI

- Apply Rodex to the surface to be cleaned.
- Apply Topper on the surface to be cleaned.
- Spray off with cold water (at maximally 35 bar)
- Treat the surface afterwards with Rodex diluted with water (1: 10)

DANE TECHNICZNE

Gęstość:	1,07 kg/l (transparent) - 1,36 kg/l (kleur)
Stopień połysku:	Polysk,Mat
Zawartość substancji stałych	
objętościowo:	56% (transparent) - 57% (kleur)

ZUŻYCIE PRAKTYCZNE

Depends on many factors, such as porosity, roughness of the surface, and material loss when applying the paint.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

Vigorously mix A and B components in the correct proportion until a homogeneous mixture is achieved.

Dilute with Coatex Speciaal Thinner maximally 10%.

Apply Coatex Speciaal NV on a surface treated with Rust-Oleum 5401.

Apply the product using a brush, spray gun, or short-haired roller.

WARUNKI APLIKACJI

Minimum ambient temperature : 10 °C

Maximum relative humidity : 80%

Minimum surface temperature : 10 °C

Maximum surface temperature: 35 °C

CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Coatex Special Thinner.

UWAGI

Dispose of remnants of the product and empty packaging as chemical waste in accordance with the local regulations and legal requirements.

INFORMACJE DOTYCZĄCE BEZPIECZEŃSTWA

Zawartość LZO:	468 g/l
Zawartość LZO w gotowej mieszance:	468 g/l
Kategoria LZO:	A/j
Limity LZO:	500 g/l
Uwagi dotyczące bezpieczeństwa:	Consult the associated product safety leaflet and the information listed on the packaging.

OKRES TRWAŁOŚCI PRODUKTU

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Data wydania: 05/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wyniknąć z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu