



COATEX SPECIAAL NV

Anti-graffiti coating in matt or gloss

- Very durable, scratch resistant, and chemically resistant
- Flexible and shock-resistant
- Does not yellow, UV resistant
- Available in matt and gloss, colourless, and with colour
- Colourless coating does not change the appearance of the surface



COATEX SPECIAAL NV

POPIS PRODUKTU (DLHÝ)

Polyurethane two-component scratch-resistant anti-graffiti coating with good chemical and mechanical resistance and colour fastness.

ODPORÚČANÉ POUŽITIE

Coatex Special NV is a durable anti-graffiti system for objects that must comply with the strictest requirements in terms of chemical and mechanical resistance.

REMOVING GRAFFITI

- Apply Rodex to the surface to be cleaned.
- Apply Topper on the surface to be cleaned.
- Spray off with cold water (at maximally 35 bar)
- Treat the surface afterwards with Rodex diluted with water (1: 10)

TECHNICAL_DATA

Hustota (g/cm³): 1,07 kg/l (transparent) - 1,36 kg/l (kleur)
Úroveň lesku: Gloss, Matt
Obsah pevných látok v objeme: 56% (transparent) - 57% (kleur)

PRAKTICKÁ VÝDATNOSŤ

Depends on many factors, such as porosity, roughness of the surface, and material loss when applying the paint.

NÁVOD NA POUŽITIE

Vigorously mix A and B components in the correct proportion until a homogeneous mixture is achieved.

Dilute with Coatex Speciaal Thinner maximally 10%.

Apply Coatex Speciaal NV on a surface treated with Rust-Oleum 5401.

Apply the product using a brush, spray gun, or short-haired roller.

PODMIENKY APLIKÁCIE

Minimum ambient temperature : 10 °C

Maximum relative humidity : 80%

Minimum surface temperature : 10 °C

Maximum surface temperature: 35 °C

ČISTENIE ZARIADENIA / POSTRIEKANIE

Coatex Special Thinner.

POZNÁMKY

Dispose of remnants of the product and empty packaging as chemical waste in accordance with the local regulations and legal requirements.

DATA_SAFETY_DATA

Úroveň VOC: 468 g/l
VOC readymix: 468 g/l
Kategória VOC: A/j
Limit VOC: 500 g/l
Poznámky k bezpečnosti: Consult the associated product safety leaflet and the information listed on the packaging.

SKLADOVATEĽNOSŤ

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

last_updated: 05/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu