



COATEX SPECIAAL NV

Anti-graffiti coating in matt or gloss

- Very durable, scratch resistant, and chemically resistant
- Flexible and shock-resistant
- Does not yellow, UV resistant
- Available in matt and gloss, colourless, and with colour
- Colourless coating does not change the appearance of the surface



COATEX SPECIAAL NV

BESKRIVNING

Polyurethane two-component scratch-resistant anti-graffiti coating with good chemical and mechanical resistance and colour fastness.

REKOMMENDERAD ANVÄNDNING

Coatex Special NV is a durable anti-graffiti system for objects that must comply with the strictest requirements in terms of chemical and mechanical resistance.

REMOVING GRAFFITI

- Apply Rodex to the surface to be cleaned.
- Apply Topper on the surface to be cleaned.
- Spray off with cold water (at maximally 35 bar)
- Treat the surface afterwards with Rodex diluted with water (1: 10)

TEKNISK DATA

Densitet: 1,07 kg/l (transparant) - 1,36 kg/l (kleur)
Glansnivå: Glans, Matt
Torrsubstansvolym: 56% (transparant) - 57% (kleur)

PRAKTISK FÖRBRUKNING

Depends on many factors, such as porosity, roughness of the surface, and material loss when applying the paint.

BRUKSANVISNING

Vigorously mix A and B components in the correct proportion until a homogeneous mixture is achieved.

Dilute with Coatex Speciaal Thinner maximally 10%.
Apply Coatex Speciaal NV on a surface treated with Rust-Oleum 5401.
Apply the product using a brush, spray gun, or short-haired roller.

APPLICERINGSFÖRHÅLLANDEN

Minimum ambient temperature : 10 °C
Maximum relative humidity : 80%
Minimum surface temperature : 10 °C
Maximum surface temperature: 35 °C

RENGÖRING AV UTRUSTNING/SPILL

Coatex Special Thinner.

ANMÄRKNINGAR

Dispose of remnants of the product and empty packaging as chemical waste in accordance with the local regulations and legal requirements.

SÄKERHETSDATA

VOC-nivå: 468 g/l
VOC färdigmix: 468 g/l
VOC-kategori: A/j
VOC-gräns: 500 g/l
Anmärkningar om säkerhet: Consult the associated product safety leaflet and the information listed on the packaging.

HÅLLBARHET

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Utgiven den: 05/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM s-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu