



## KURALTEX BL 314

# Transparent protective agent

- Protects surfaces without changing the appearance
- Excellent dirt repellent action
- Resistant to UV radiation and weather
- Flexible layer does not crack or tear
- For aluminium, plastics, and coated metals

# KURALTEX BL 314

## POPIS PRODUKTU (DLOUHÝ)

A concentrated protective agent based on acrylic copolymers and polythene additives for anodised aluminium, coated metal surfaces, and a variety of plastics.

## DOPORUČENÉ POUŽITÍ

Kuraltex BL 314 is suitable as a limited-lifespan protection for anodised aluminium, coated metal surfaces, and plastics.

## DOPORUČENÝ SYSTÉM

First layer : Kuraltex BL 314 of Kuraltex Primer

Second layer : Kuraltex BL 314

Remove with : Vetclean of Vanex

## TECHNICAL DATA

Hustota (g/cm<sup>3</sup>): 1,02 kg/l

Obsah pevných látek v objemu: 50%

## DRY TIMES BY 20

Dotykem suché: 15 minutes

Suché na manipulaci: 30 minutes

Suchý nátěr: N/A

Plně vytvrzené: N/A

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

50 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

25 µm

## PRAKTICKÁ SPOTŘEBA

The actual consumption is dependent on the method of application.

## NÁVOD K POUŽITÍ

- Degrease, clean, and dry the surface
- Shake Kuraltex BL 314 before use
- Dilute the product with maximally 10% water
- Apply the product very thinly using a soaper ('scrubby'), sponge, or spray gun and distribute it evenly over the surface

## PODMÍNKY POUŽITÍ

Minimum ambient temperature : 10°C

Maximum relative humidity : 90%

Minimum surface temperature : 10 °C\*

Maximum surface temperature: 35 °C

\* When applying a coating and during the drying phase, the surface temperature must be at least 3 °C above the dew point.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

Rinse with clean water immediately after use.

## PH

6,50

## DOBA POUŽITELNOSTI

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

last\_updated: 05/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu