



KURALTEX BL 314

Transparent protective agent

- Protects surfaces without changing the appearance
- Excellent dirt repellent action
- Resistant to UV radiation and weather
- Flexible layer does not crack or tear
- For aluminium, plastics, and coated metals

KURALTEX BL 314

POPIS PRODUKTU (DLHÝ)

A concentrated protective agent based on acrylic copolymers and polythene additives for anodised aluminium, coated metal surfaces, and a variety of plastics.

ODPORÚČANÉ POUŽITIE

Kuraltex BL 314 is suitable as a limited-lifespan protection for anodised aluminium, coated metal surfaces, and plastics.

ODPORÚČANÝ SYSTÉM

First layer : Kuraltex BL 314 of Kuraltex Primer

Second layer : Kuraltex BL 314

Remove with : Vetclean of Vanex

TECHNICAL DATA

Hustota (g/cm³): 1,02 kg/l

Obsah pevných látok v objeme: 50%

DRY TIMES BY 20

Na dotyk suché: 15 minutes

Suché na manipuláciu: 30 minutes

Suchý na opätovné natieranie: N/A

Úplne vytvrdnuté: N/A

ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

50 µm

ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

25 µm

PRAKTICKÁ VÝDATNOSŤ

The actual consumption is dependent on the method of application.

NÁVOD NA POUŽITIE

- Degrease, clean, and dry the surface
- Shake Kuraltex BL 314 before use
- Dilute the product with maximally 10% water
- Apply the product very thinly using a soaper ('scrubby'), sponge, or spray gun and distribute it evenly over the surface

PODMIENKY APLIKÁCIE

Minimum ambient temperature : 10°C

Maximum relative humidity : 90%

Minimum surface temperature : 10 °C*

Maximum surface temperature: 35 °C

* When applying a coating and during the drying phase, the surface temperature must be at least 3 °C above the dew point.

ČISTENIE ZARIADENIA / POSTRIEKANIE

Rinse with clean water immediately after use.

PH

6,50

SKLADOVATEĽNOSŤ

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

last_updated: 05/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu