



**PROCHEMKO**



## **POLITEX**

---

# **Concentrated floor wax for refreshing old linoleum**

- Effective dirt and water repellence
- Restores shine
- Good wear resistance
- Resists UV, does not yellow
- Ideal for old or worn linoleum

# POLITEX

## OPIS

A concentrated floor wax based on acrylate polymers, special waxes and other additives for rubber, linoleum, unglazed floor tiles, concrete floors, washed gravel tile floors and cork.

## ZAŁECANE UŻYCIE

Shiny floor wax for synthetic floors such as rubber, linoleum and such like, unglazed floor tiles, concrete floors, coated floors, washed gravel tile floors and cork. (not to be used on Pegulan, Mipolan or wooden floors)

## DANE TECHNICZNE

Gęstość: 1,02 kg/l  
Zawartość substancji stałych  
objętościowo: 21%

## CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk: 30 min  
Do użytku: 1.5 h

## ZAŁECANA GRUBOŚĆ WARSTWY NA MOKRO

100 µm (undiluted), 80 µm (diluted)

## ZAŁECANA GRUBOŚĆ WARSTWY NA SUCHO

20 µm (undiluted), 10 µm (diluted)

## ZUŻYCIE TEORETYCZNE

10 m<sup>2</sup>/l. (undiluted)

## ZUŻYCIE PRAKTYCZNE

In practice the consumption depends on the roughness of the surface and the desired appearance.

## PRZYGOTOWANIE POWIERZCHNI

Dust off the surface and make it clean and dry.

## WSKAZÓWKI DOTYCZĄCE UŻYCIA

Dilute Politex with water to a maximum of 1 : 2.5 (too much dilution hinders film formation). Apply the product in two layers, crossways, using a soaper. Allow the first layer to dry for at least 6 -8 hours before applying the second layer. To acquire the best possible shine use Politex diluted with water in the ratio 1 : 2.5 and apply with the help of a misting nozzle and a high speed machine. (minimum 2000 t/min)

## WARUNKI APLIKACJI

Minimum ambient temperature: 10°C  
Maximum relative humidity: 90%  
Minimum surface temperature: 10°C  
Maximum surface temperature: 35°C

## CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Rinse with clean water directly after use.

## UWAGI

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

## PH

8

## OKRES TRWAŁOŚCI PRODUKTU

Minimum of 12 months when stored in a dry, cool and frost-free environment in the original, unopened packaging.

Data wydania: 05/02/2025

**Dostępne kolory i opakowania:** Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej [www.rust-oleum.eu](http://www.rust-oleum.eu).

**Zrzeczenie się:** Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wynikać z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu