



**PROCHEMKO**



## **POLITEX**

---

# **Concentrated floor wax for refreshing old linoleum**

- Effective dirt and water repellence
- Restores shine
- Good wear resistance
- Resists UV, does not yellow
- Ideal for old or worn linoleum

# POLITEX

## POPIS PRODUKTU (DLHÝ)

A concentrated floor wax based on acrylate polymers, special waxes and other additives for rubber, linoleum, unglazed floor tiles, concrete floors, washed gravel tile floors and cork.

## ODPORÚČANÉ POUŽITIE

Shiny floor wax for synthetic floors such as rubber, linoleum and such like, unglazed floor tiles, concrete floors, coated floors, washed gravel tile floors and cork. (not to be used on Pegulan, Mipolan or wooden floors)

## TECHNICAL DATA

Hustota (g/cm<sup>3</sup>): 1,02 kg/l  
Obsah pevných látok v objeme: 21%

## DRY TIMES BY 20

Na dotyk suché: 30 min  
Suché na manipuláciu: 1.5 h

## ODPORÚČANÁ HRúbKA MOKRÉHO FILMU

100 µm (undiluted), 80 µm (diluted)

## ODPORÚČANÁ HRúbKA SUCHÉHO FILMU

20 µm (undiluted), 10 µm (diluted)

## TEORETICKÁ SPOTREBA

10 m<sup>2</sup>/l. (undiluted)

## PRAKTICKÁ VÝDATNOSŤ

In practice the consumption depends on the roughness of the surface and the desired appearance.

## PRÍPRAVA POVRCHU

Dust off the surface and make it clean and dry.

## NÁVOD NA POUŽITIE

Dilute Politex with water to a maximum of 1 : 2.5 (too much dilution hinders film formation). Apply the product in two layers, crossways, using a soaper. Allow the first layer to dry for at least 6 -8 hours before applying the second layer. To acquire the best possible shine use Politex diluted with water in the ratio 1 : 2.5 and apply with the help of a misting nozzle and a high speed machine. (minimum 2000 t/min)

## PODMIENKY APLIKÁCIE

Minimum ambient temperature: 10°C  
Maximum relative humidity: 90%  
Minimum surface temperature: 10°C  
Maximum surface temperature: 35°C

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Rinse with clean water directly after use.

## POZNÁMKY

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

## PH

8

## SKLADOVATEĽNOSŤ

Minimum of 12 months when stored in a dry, cool and frost-free environment in the original, unopened packaging.

last\_updated: 05/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu