

PROCHEMKO



PREVOSIL AS

Stone and grouting reinforcer and hydrophobic agent

- Wetting-effect and long-lasting run off effect
- Reinforces loose grouting
- Penetrates deeply into the surface
- Vapour permeable
- Ideal for weathered grouting, flaky brick and natural stone and dried out walls

WWW.PROCHEMKO.EU

PREVOSIL AS

DESCRIZIONE

Hydrophobic treatment with (joint) strengthening properties based on siloxanes and alcohol for mineral, porous surfaces such as grouting/masonry.

UTILIZZO CONSIGLIATO

Reinforcing and giving hydrophobic treatment to sandy and eroded grouting, flaky brick and natural stone and dried out walls.

DATI TECNICI

Densità: 0,85 kg/l
Residuo secco in peso: 8,5%

TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: N/A
Asciutto da rivestire: N/A
Completamente indurito: N/A

CONSUMO TEORICO

0.7 - 2 m²/l

CONSUMO PRATICO

It is advisable to carry out a test beforehand in order to assess the right consumption level.

ISTRUZIONI PER L'USO

The surfaces to be treated need to be free of dust and grease. Any silted surfaces should first be treated with Prevosil® CE. Application in two layers wet in wet, taking account of the surface's absorbency, and apply from bottom to top. The penetration of Prevosil® AS is crucial for a long-lasting effect. Avoid using when the full sun is shining on the façade. During use, avoid open fire, sparks and heat sources. During application, protect material in the vicinity, such as window frames, windows and plants.

CONDIZIONI DI APPLICAZIONE

Minimum ambient temperature: 5°C
Maximum relative humidity: 100%
Minimum surface temperature: 5°C
Maximum surface temperature: 25°C

PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Rinse with Isopropyl alcohol directly after use.

NOTE

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

SCADENZA

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Data del rilascio: 05/02/2025

Colori e formati di confezione disponibili: Si prega di consultare la pagina relativa al prodotto su www.rust-oleum.eu per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

Dichiarazione di non responsabilità: Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da www.rust-oleum.eu o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu