



PREVOSIL AS

Stone and grouting reinforcer and hydrophobic agent

- Wetting-effect and long-lasting run off effect
- Reinforces loose grouting
- Penetrates deeply into the surface
- Vapour permeable
- Ideal for weathered grouting, flaky brick and natural stone and dried out walls

PREVOSIL AS

POPIS PRODUKTU (DLHÝ)

Hydrophobic treatment with (joint) strengthening properties based on siloxanes and alcohol for mineral, porous surfaces such as grouting/masonry.

ODPORÚČANÉ POUŽITIE

Reinforcing and giving hydrophobic treatment to sandy and eroded grouting, flaky brick and natural stone and dried out walls.

TECHNICAL DATA

Hustota (g/cm ³):	0,85 kg/l
Obsah pevných látok v hmotnosti:	8,5%

DRY_TIMES_BY_20

Na dotyk suché:	N/A
Suchý na opäťovné natieranie:	N/A
Úplne vytvrdenuté:	N/A

TEORETICKÁ SPOTREBA

0.7 - 2 m²/l

PRAKTICKÁ VÝDATNOSŤ

It is advisable to carry out a test beforehand in order to assess the right consumption level.

NÁVOD NA POUŽITIE

The surfaces to be treated need to be free of dust and grease. Any silted surfaces should first be treated with Prevosil® CE. Application in two layers wet in wet, taking account of the surface's absorbency, and apply from bottom to top. The penetration of Prevosil® AS is crucial for a long-lasting effect. Avoid using when the full sun is shining on the façade. During use, avoid open fire, sparks and heat sources. During application, protect material in the vicinity, such as window frames, windows and plants.

PODMIENKY APLIKÁCIE

Minimum ambient temperature: 5°C
Maximum relative humidity: 100%
Minimum surface temperature: 5°C
Maximum surface temperature: 25°C

ČISTENIE ZARIADENIA / POSTRIEKANIE

Rinse with Isopropyl alcohol directly after use.

POZNÁMKY

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

SKLADOVATEĽNOSŤ

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

last_updated: 05/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shandon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu