

PROCHEMKO



PREVOSIL AS

Stone and grouting reinforcer and hydrophobic agent

- Wetting-effect and long-lasting run off effect
- Reinforces loose grouting
- Penetrates deeply into the surface
- Vapour permeable
- Ideal for weathered grouting, flaky brick and natural stone and dried out walls

WWW.PROCHEMKO.EU

PREVOSIL AS

BESKRIVNING

Hydrophobic treatment with (joint) strengthening properties based on siloxanes and alcohol for mineral, porous surfaces such as grouting/masonry.

REKOMMENDERAD ANVÄNDNING

Reinforcing and giving hydrophobic treatment to sandy and eroded grouting, flaky brick and natural stone and dried out walls.

TEKNISK DATA

Densitet: 0,85 kg/l
Torrsubstansvikt: 8,5%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr: N/A
Övermålningsbar: N/A
Fullt härdad: N/A

TEORETISK FÖRBRUKNING

0.7 - 2 m²/l

PRAKTISK FÖRBRUKNING

It is advisable to carry out a test beforehand in order to assess the right consumption level.

BRUKSANVISNING

The surfaces to be treated need to be free of dust and grease. Any silted surfaces should first be treated with Prevosil® CE. Application in two layers wet in wet, taking account of the surface's absorbency, and apply from bottom to top. The penetration of Prevosil® AS is crucial for a long-lasting effect. Avoid using when the full sun is shining on the façade. During use, avoid open fire, sparks and heat sources. During application, protect material in the vicinity, such as window frames, windows and plants.

APPLICERINGSFÖRHÅLLANDEN

Minimum ambient temperature: 5°C
Maximum relative humidity: 100%
Minimum surface temperature: 5°C
Maximum surface temperature: 25°C

RENGÖRING AV UTRUSTNING/SPILL

Rinse with Isopropyl alcohol directly after use.

ANMÄRKNINGAR

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

HÅLLBARHET

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Utgivet den: 05/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu