



PROCHEMKO



PREVOSIL SPECIAAL WB

Makes mineral surfaces such as facades water repellent

- Very high percentage of active components
- Penetrates deep into the surface
- Vapour permeable system prevents frost damage
- Alkali resistant
- Ideal for brick, concrete, natural stone, aerated concrete and more

WWW.PROCHEMKO.EU

PREVOSIL SPECIAAL WB

OPIS

Hydrophobic treatment with high levels of active components based on a water dispersion of silanes/siloxanes for mineral, porous surfaces.

ZAŁECANE UŻYCIE

As a hydrophobic treatment for masonry, concrete, calcium silicate, mineral grouting and lightly porous natural stone.

DANE TECHNICZNE

Gęstość: 1,0 kg/l
Zawartość substancji stałych w wagowo: 7%

CZAS SCHNIĘCIA PRZY 20°C/RH 50%

Na dotyk: N/A
Do przemalowania: N/A
Pełne utwardzenie: N/A

ZUŻYCIE TEORETYCZNE

0.7 - 2 m²/l

ZUŻYCIE PRAKTYCZNE

We advise carrying out test before commencing activity in order to assess the right consumption level.

WSKAZÓWKI DOTYCZĄCE UŻYCIA

The surfaces to be treated need to be free of dust and grease. Prevosil Special WB does not fill gaps; any pointing in poor condition should be repaired beforehand. Any silted surfaces should first be treated with Prevosil CE. Application in two layers wet in wet, taking account of the surface's absorbency, and apply from bottom to top. During application, protect material in the vicinity, such as window frames, windows and plants. Apply Prevosil Special WB using the flow-coat system. (low pressure avoiding mist formation)

WARUNKI APLIKACJI

Minimum ambient temperature: 5°C
Maximum relative humidity: 100%
Minimum surface temperature: 5°C
Maximum surface temperature: 35°C

CZYSZCZENIE NARZĘDZI / ZABRUDZEŃ

Rinse with water directly after use.

UWAGI

Certification report HD 340/133-14 from the Scientific and Technical Centrum for the construction industry in Brussels. Certification report R/25811/88 from the KU Leuven, Laboratorium Reyntjes in Leuven. Available on request.

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

PH

7

OKRES TRWAŁOŚCI PRODUKTU

Can be stored for a minimum of 12 months in a cool, dry and frost-free environment in the original, unopened packaging.

Data wydania: 05/02/2025

Dostępne kolory i opakowania: Więcej informacji na temat dostępnych kolorów i opakowań na stronie internetowej www.rust-oleum.eu.

Zrzeczenie się: Informacje tu zawarte przekazywane są w dobrej wierze, bez udzielania gwarancji. Ponieważ warunki aplikacji są poza naszą kontrolą, Rust-Oleum nie może ponosić jakiegokolwiek odpowiedzialności lub obciążeń finansowych, które mogą wyniknąć z niewłaściwego zastosowania tego produktu. Produkt musi być przechowywany, transportowany i aplikowany zgodnie z zaleceniami Rust-Oleum. Użytkownik powinien zadbać o posiadanie najbardziej aktualnej karty produktu. Wszystkie karty dostępne są na stronie internetowej producenta lub dystrybutora. Firma zastrzega sobie prawo modyfikowania danych bez uprzedzenia.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu