



PREVOSIL SPECIAAL WB

**Makes mineral surfaces such as
facades water repellent**

- Very high percentage of active components
- Penetrates deep into the surface
- Vapour permeable system prevents frost damage
- Alkali resistant
- Ideal for brick, concrete, natural stone, aerated concrete and more

PREVOSIL SPECIAAL WB

POPIS PRODUKTU (DLHÝ)

Hydrophobic treatment with high levels of active components based on a water dispersion of silanes/siloxanes for mineral, porous surfaces.

ODPORÚČANÉ POUŽITIE

As a hydrophobic treatment for masonry, concrete, calcium silicate, mineral grouting and lightly porous natural stone.

TECHNICAL DATA

Hustota (g/cm ³):	1,0 kg/l
Obsah pevných látok v hmotnosti:	7%

DRY_TIMES_BY_20

Na dotyk suché:	N/A
Suchý na opäťovné natieranie:	N/A
Úplne vytvrdené:	N/A

TEORETICKÁ SPOTREBA

0.7 - 2 m²/l

PRAKTIKÁ VÝDATNOSŤ

We advise carrying out test before commencing activity in order to assess the right consumption level.

NÁVOD NA POUŽITIE

The surfaces to be treated need to be free of dust and grease. Prevosil Special WB does not fill gaps; any pointing in poor condition should be repaired beforehand. Any silted surfaces should first be treated with Prevosil CE. Application in two layers wet in wet, taking account of the surface's absorbency, and apply from bottom to top. During application, protect material in the vicinity, such as window frames, windows and plants. Apply Prevosil Special WB using the flow-coat system. (low pressure avoiding mist formation)

PODMIENKY APLIKÁCIE

Minimum ambient temperature: 5°C
Maximum relative humidity: 100%
Minimum surface temperature: 5°C
Maximum surface temperature: 35°C

ČISTENIE ZARIADENIA / POSTRIEKANIE

Rinse with water directly after use.

POZNÁMKY

Certification report HD 340/133-14 from the Scientific and Technical Centrum for the construction industry in Brussels. Certification report R/25811/88 from the KU Leuven, Laboratorium Reytjes in Leuven. Available on request.

Dispose of remaining product and empty packaging as chemical waste, in accordance with the local regulations and legal requirements.

PH

7

SKLADOVATEĽNOSŤ

Can be stored for a minimum of 12 months in a cool, dry and frost-free environment in the original, unopened packaging.

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
36, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zellem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

last_updated: 05/02/2025