

PROCHEMKO



ZYLOX

Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

WWW.PROCHEMKO.EU

ZYLOX

BESKRIVELSE

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

ANBEFALET BRUG

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

TEKNISK DATA

Tæthed:	1,0 kg/l
Glansgrad:	Mat
Tørstofindhold i volumen:	10%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringsstør:	1 hour
Genbehandlingstør:	1 hour
Fuldt hærdet:	3 - 4 days

TEORETISK FORBRUG

ANTI-GRAFFITI: 3 - 5 m²/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.
IMPREGNATOR: 10 - 20 m²/L. Consumption strongly depends on the absorbency of the substrate.

PRAKTISK FORBRUG

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

BRUGSANVISNING

The surfaces to be treated must be wind dried, dustless, and free of grease.

Do not apply in direct sunlight or on hot surfaces.

Stir or shake the Zylox well before use.

ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.

IMPREGNATOR: Dilute Zylox with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

ANVENDELSBETINGELSER

Minimum ambient temperature : 5 °C

Maximum relative humidity : 70%

Minimum surface temperature : 5 °C

Maximum surface temperature: 25 °C

RENGØRING AF Udstyr/SPILD

Rinse with water immediately after use.

BEMÆRKNINGER

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.

Treat empty packaging as industrial waste unless well cleaned and dry.

Do not dispose of clean packaging as chemical waste.

SIKKERHEDSDATA

VOC-niveau:	51 g/l
VOC-færdigblanding:	51 g/l
VOC-kategori:	A/i
VOC-grænse:	140 g/l

PH

5

HOLDBARHED

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Udstedelsesdato: 16/05/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu