

**PROCHEMKO**



**ZYLOX**

## Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

[WWW.PROCHEMKO.EU](http://WWW.PROCHEMKO.EU)

# ZYLOX

## DESCRIZIONE

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

## UTILIZZO CONSIGLIATO

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

## DATI TECNICI

Densità: 1,0 kg/l  
Livello di lucentezza: Opaco  
Residuo secco in volume: 10%

## TEMPI DI ASCIUGATURA A 20°C/UR 50%

Asciutto al tatto: 1 hour  
Asciutto da rivestire: 1 hour  
Completamente indurito: 3 - 4 days

## CONSUMO TEORICO

ANTI-GRAFFITI: 3 - 5 m<sup>2</sup>/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.  
IMPREGNATOR: 10 - 20 m<sup>2</sup>/L. Consumption strongly depends on the absorbency of the substrate.

## CONSUMO PRATICO

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

## ISTRUZIONI PER L'USO

The surfaces to be treated must be wind dried, dustless, and free of grease.

Do not apply in direct sunlight or on hot surfaces.

Stir or shake the Zyxol well before use.

ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.

IMPREGNATOR: Dilute Zyxol with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

## CONDIZIONI DI APPLICAZIONE

Minimum ambient temperature : 5 °C  
Maximum relative humidity : 70%  
Minimum surface temperature : 5 °C  
Maximum surface temperature: 25 °C

## PULITURA DELLE ATTREZZATURE / DEGLI SVERSAMENTI

Rinse with water immediately after use.

## NOTE

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.

Treat empty packaging as industrial waste unless well cleaned and dry.

Do not dispose of clean packaging as chemical waste.

## DATI RELATIVI ALLA SICUREZZA

Livello di COV: 51 g/l  
Soluzione premiscelata COV: 51 g/l  
Categoria COV: A/i  
Limite di COV: 140 g/l

## PH

5

## SCADENZA

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Data del rilascio: 05/02/2025

**Colori e formati di confezione disponibili:** Si prega di consultare la pagina relativa al prodotto su [www.rust-oleum.eu](http://www.rust-oleum.eu) per una visione complessiva dei colori e dei formati di confezione effettivamente disponibili.

**Dichiarazione di non responsabilità:** Le informazioni contenute nel presente documento sono al meglio della nostra conoscenza, vere e accurate e sono fornite in buona fede ma senza garanzia. L'utente sarà ritenuto soddisfatto/a indipendentemente dall'idoneità dei nostri prodotti per il suo proprio scopo particolare. In nessun caso Rust-Oleum Europe potrà essere ritenuta responsabile per danni consequenziali o incidentali. I prodotti devono essere conservati, maneggiati e applicati in condizioni conformi alle raccomandazioni dettagliate di Rust-Oleum Europe contenute nella copia più recente della scheda tecnica del prodotto. È responsabilità dell'utente accertarsi di disporre della copia attuale. Le copie più recenti della scheda tecnica del prodotto sono disponibili gratuitamente e scaricabili da [www.rust-oleum.eu](http://www.rust-oleum.eu) o a fronte di richiesta al nostro servizio clienti. Rust-Oleum Europe si riserva il diritto di modificare le proprietà dei suoi prodotti senza alcun preavviso.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu