

**PROCHEMKO**



**ZYLOX**

## Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

[WWW.PROCHEMKO.EU](http://WWW.PROCHEMKO.EU)

# ZYLOX

## POPIS PRODUKTU (DLHÝ)

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

## ODPORUČANÉ POUŽITIE

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

## TECHNICAL\_DATA

Hustota (g/cm<sup>3</sup>): 1,0 kg/l  
Úroveň lesku: Matt  
Obsah pevných látok v objeme: 10%

## DRY\_TIMES\_BY\_20

Na dotyk suché: 1 hour  
Suchý na opätovné natieranie: 1 hour  
Úplne vytvrdené: 3 - 4 days

## TEORETICKÁ SPOTREBA

ANTI-GRAFFITI: 3 - 5 m<sup>2</sup>/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.  
IMPREGNATOR: 10 - 20 m<sup>2</sup>/L. Consumption strongly depends on the absorbency of the substrate.

## PRAKTICKÁ VÝDATNOSŤ

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

## NÁVOD NA POUŽITIE

The surfaces to be treated must be wind dried, dustless, and free of grease.

Do not apply in direct sunlight or on hot surfaces.

Stir or shake the Zylox well before use.

ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.

IMPREGNATOR: Dilute Zylox with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

## PODMIENKY APLIKÁCIE

Minimum ambient temperature : 5 °C  
Maximum relative humidity : 70%  
Minimum surface temperature : 5 °C  
Maximum surface temperature: 25 °C

## ČISTENIE ZARIADENIA / POSTRIEKANIE

Rinse with water immediately after use.

## POZNÁMKY

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.

Treat empty packaging as industrial waste unless well cleaned and dry.

Do not dispose of clean packaging as chemical waste.

## DATA SAFETY DATA

Úroveň VOC: 51 g/l  
VOC readymix: 51 g/l  
Kategória VOC: A/i  
Limit VOC: 140 g/l

## PH

5

## SKLADOVATEĽNOSŤ

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

last\_updated: 05/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu