

PROCHEMKO



ZYLOX

Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

WWW.PROCHEMKO.EU

ZYLOX

BESKRIVNING

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

REKOMMENDERAD ANVÄNDNING

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

TEKNISK DATA

Densitet: 1,0 kg/l
Glansnivå: Matt
Torrsubstansvolym: 10%

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstid: 1 hour
Övermålningsbar: 1 hour
Fullt härdad: 3 - 4 days

TEORETISK FÖRBRUKNING

ANTI-GRAFFITI: 3 - 5 m²/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.
IMPREGNATOR: 10 - 20 m²/L. Consumption strongly depends on the absorbency of the substrate.

PRAKTISK FÖRBRUKNING

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

BRUKSANVISNING

The surfaces to be treated must be wind dried, dustless, and free of grease.

Do not apply in direct sunlight or on hot surfaces.

Stir or shake the Zyxol well before use.

ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.

IMPREGNATOR: Dilute Zyxol with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

APPLICERINGSFÖRHÅLLANDEN

Minimum ambient temperature : 5 °C
Maximum relative humidity : 70%
Minimum surface temperature : 5 °C
Maximum surface temperature: 25 °C

RENGÖRING AV UTRUSTNING/SPILL

Rinse with water immediately after use.

ANMÄRKNINGAR

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.

Treat empty packaging as industrial waste unless well cleaned and dry.

Do not dispose of clean packaging as chemical waste.

SÄKERHETSDATA

VOC-nivå: 51 g/l
VOC färdigmix: 51 g/l
VOC-kategori: A/i
VOC-gräns: 140 g/l

PH

5

HÅLLBARHET

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Utgivet den: 05/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskadorna. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM s-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu